



PT. GYUNG DO INDONESIA

PAINT FOR WOOD, PLASTIC, METAL & FLOOR

UNSATURATED POLYESTER SURFACER

GPA – 2730R-00 / GPH – 006J / GPN – N - 500

Product Information

This product is 3 components unsaturated polyester surfacer based on polyester resin. It has good hardness, curing, sanding, high build properties.

Recommended Use

For wood

Technical Data

Appearance	Viscous White Liquid
Sp. Gr. (gr/cm³, 32°C)	1.6~1.7/0.9~1.0/1.1/1.2 (Base/Promotor/Catalyst)
Drying Time (32°C)	4~6 hrs.
Application	Spray / Brush
Spray Viscosity (NK2,32°C)	35~45 sec.
Theoretical Coverage (mix)	5m ² /lt (DFT 200µm, WET 210 µm)
Thinner	GPT-040
Gloss (60°)	Matt
Flash Point (°C)	About 31
Mixing ratio (by wt)	100 : 1 : 1 (Base / promotor / Catalyst)
Solid Content (%) (mix)	95±1

Surface Preparation

Remove oil, water, and dust.

Precaution

1. After application, close the container tightly.
2. Have to use urethane sealer for good adhesion.
3. When you store, have to separate promotor and catalyst.

