



PT. GYUNG DO INDONESIA

PAINT FOR WOOD, PLASTIC, METAL & FLOOR

EPOXY MORTAR PRIMER

GHDS – 2400 CLEAR / GEH - 007

Product Information

This product is 2 components epoxy mortar clear based on epoxy resin, polyamide resin. It has good curing, water and alkali resist, adhesion properties. It can mix silica (30~80 mesh)

Recommended Use

For concret (primer, mortar, top coat)

Technical Data

Appearance	Viscous Transparent Liquid
Sp. Gr. (gr/cm³, 32°C)	1.1~1.2/0.9~1.0(Base/Hardener)
Drying Time (32°C)	12~16 hrs.
Application	Scraper, Brush, Roller
Spray Viscosity (NK2,32°C)	No thinning
Theoretical Coverage (mix)	0.5 kg / m ² (0.5mm) - Clear 6.3 kg / m ² (3mm) - Mortar
Thinner	Epoxy Thinner
Gloss (60°)	Full gloss
Flash Point (°C)	About 65
Hardener	GEH-007
Mixing ratio (by wt)	2 : 1 : 15 (Base/Hardener/silica)
Pot life (32°C)	20 ~ 30 min.
Solid Content (%) (mix)	99±1

Surface Preparation

1. Remove oil, water, and dust.
2. Grind concrete.

Precaution

1. After application, close the container tightly.