



PT. GYUNG DO INDONESIA
PAINT FOR WOOD, PLASTIC, METAL & FLOOR

STOVING ALKYD PRIMER

MSP – 21 - 88

Product Information

This product is 1 components stoving alkyd primer based on alkyd resin, amino resin. It has good hardness, curing.

Recommended Use

For steel

Technical Data

Appearance	Viscous White Liquid
Sp. Gr. (gr/cm³, 32°C)	1.2~1.3
Drying Time (32°C)	150°C x 30 min.
Application	Spray
Spray Viscosity (NK2,32°C)	11~13
Theoretical Coverage	14 m ² /lt (DFT 40µm, WET 90)
Thinner	Stoving Thinner
Gloss (60°)	Semi gloss
Flash Point (°C)	About 25
Solid Content (%)	70±1

Surface Preparation

Remove oil, water, and dust.

Precaution

1. After application, close the container tightly.