

# ALKYD URETHANE SANDING SEALER HUS – 1900 CLEAR / HAD – 001CRP

# **Product Information**

This product is 2 components urethane sanding sealer clear based on alkyd resin, polyisocyanate.

It has good hardness, drying, sanding properties.

### **Recommended Use**

For wood

# **Technical Data**

Appearance	Viscous Milky Liquid
Sp. Gr. (gr/cm³, 32°C)	1.0~1.1 / 0.9~1.0 (Base/Hardener)
Drying Time (32°C)	1~2 hrs.
Application	Spray, Brush
Spray Viscosity (NK2,32°c)	11~13
Theoretical Coverage (mix)	10 m²/lt (DFT 50µm, WET 100)
Thinner	Urethane Thinner
Gloss (60°)	Semi gloss
Flash Point (°C )	About -4
Hardener	HAD-001CRP
Mixing ratio ( by wt )	2 : 1 ( Base / Hardener )
Solid Content (%) (mix)	57±1

### **Surface Preparation**

Remove oil, water, and dust.

#### Precaution

1. After application, close the container tightly.