

EPOXY MASTIC COLOR GHDF – 3400 - 00 / GEH - 017

Product Information

GYUNG DO PAINT

This product is 2 components epoxy mastic color based on epoxy resin, polyamide resin. It has good curing, water and alkali resist, anticorrosive, high build, adhesion properties.

Recommended Use

For concret, steel

Technical Data

Appearance	Viscous White Liquid
Sp. Gr. (gr/cm ³ , 32°C)	1.6~1.7/0.9~1.0(Base/Hardener)
Drying Time (32°C)	8~10 hrs.
Application	Spray, Brush, Roller
Spray Viscosity (NK2,32°c)	11~13
Theoretical Coverage (mix)	6 m²/lt (DFT 100μm, WET 170μm)
Thinner	Epoxy Thinner
Gloss (60°)	Semi gloss
Flash Point (°C)	About 25
Hardener	GEH-017
Mixing ratio (by wt)	4:1 (Base / Hardener)
Solid Content (%) (mix)	75±1

Surface Preparation

Remove oil, water, and dust.

Precaution

1. After application, close the container tightly.