



PT. GYUNG DO INDONESIA

PAINT FOR WOOD, PLASTIC, METAL & FLOOR

STOVING ALKYD TOP COAT CLEAR MSV – 224 CLEAR

Product Information

This product is 1 components stoving alkyd top coat clear based on alkyd resin, amino resin.

It has good hardness, curing.

Recommended Use

For steel

Technical Data

Appearance	Viscous Transparent Liquid
Sp. Gr. (gr/cm³, 32°C)	1.0~1.1
Drying Time (32°C)	150°C x 30 min.
Application	Spray
Spray Viscosity (NK2,32°C)	11~13
Theoretical Coverage	10 m ² /lt (DFT 50µm, WET 100)
Thinner	Stoving Thinner
Gloss (60°)	Full gloss
Flash Point (°C)	About 25
Solid Content (%)	57±1

Surface Preparation

Remove oil, water, and dust.

Precaution

1. After application, close the container tightly.